

Trade name: **SIMONA®CPVC CORZAN Industrial Grade (pressed)**
 Date of printing: 06.07.2017

Revision: 10.01.2017

SIMONA®CPVC CORZAN Industrial Grade (pressed)	
Data sheet update	10.01.2017
Moulding compound extruded (Welding Rod)	CPVC LCDPS 110-25-T28
Extruded to moulding compound standard	In Anlehnung an DIN EN ISO 1163-1
Moulding compound pressed	CPVC, QP, 106-25-T28
Pressed to moulding compound standard	In Anlehnung an DIN EN ISO 1163-1
Density, g/cm ³ , DIN EN ISO 1183	1.50
Tensile modulus of elasticity, MPa, DIN EN ISO 527	2500
Yield stress, MPa, DIN EN ISO 527	51
Elongation at yield, % , DIN EN ISO 527	3
Impact strength, kJ/m ² , DIN EN ISO 179	without break
Notched impact strength, kJ/m ² , DIN EN ISO 179	8
Shore hardness D (15 s), DIN EN ISO 868	80
Mean coefficient of linear thermal expansion, K ⁻¹ , ISO 11359-2	0,7 x 10 ⁻⁴
Vicat B, °C , DIN EN ISO 306	107
Surface resistivity, Ohm , DIN IEC 60093	10 ¹⁵
Temperature range, °C	-40 to +95
Fire behaviour DIN 4102	DIN 4102 B1 low flammability (self-assessment without test certificate)
Physiological safety in accordance with BfR (German Federal Institute for risk valuation)	no

All specifications are deemed to be approximate values in respect of the specific material and may vary depending on the processing methods used. In general, data specified applies to average values measured on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations from the values specified are possible if the sheets in this thickness are not available. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Information presented herein is not necessarily applicable to other products (e.g. pipes, solid rods) of the same material or products that have undergone downstream processing. Suitability of materials for a specific field of application must be assessed by the party responsible for processing or the end-user. All technical specifications presented herein are designed merely to provide

**SIMONA®CPVC CORZAN Industrial
Grade (pressed)**

assistance in terms of project planning. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at tsc@simona.de.